






Customer Service: +1 570-645-6917 Toll Free: 1 800-441-7777

www.ametekfpp.com • info.fpp@ametek.com

ULTRA HIGH PURITY TUBING AND PIPE



Fluoropolymer Pipe

Fluoropolymer pipe has been added to AMETEK's family of fluoropolymer products. AMETEK offers Schedule 40 and 80 pipe in your choice of FEP, PFA, and UHP. These resins are an excellent choice for a wide range of high purity and corrosive chemicals covering temperature ranges from -100° to 400°F. All can be produced in standard straight lengths of 10 feet, or are available as custom lengths up to 20 feet. High purity pipe is capped and wrapped in plastic sleeves prior to shipment. All pipe is natural in color.



TYPICAL MATERIAL PROPERTIES								
Properties	Units	FEP	PFA	UHP	PVDF			
Melting Point	°C	260	305	305	173			
Specific Gravity	-	2.14	2.15	2.15	1.78			
Tensile Strength (break)	psi	4300	4000	4000	6500			
Elongation (break)	%	350	300	300	5-10			

Standard Pipe Sizes

Schedule #40

IDC	SIZE	WALL		
IPS	I.D.	0.D.	THICKNESS	
1/8	0.269	0.405	0.068	
1/4	0.364	0.540	0.088	
3/8	0.493	0.675	0.091	
1/2	0.622	0.840	0.109	
3/4	0.824	1.050	0.113	
1	1.049	1.315	0.133	
1 1/4	1.380	1.660	0.140	
1 1/2	1.610	1.900	0.145	
2	2.067	2.375	0.154	
2 1/2	2.469	2.875	0.203	
3	3.068	3.500	0.216	

Schedule #80

IPS	SIZE	WALL	
IFS	I.D.	0.D.	THICKNESS
1/8	0.215	0.405	0.095
1/4	0.302	0.540	0.119
3/8	0.423	0.675	0.126
1/2	0.546	0.840	0.147
3/4	0.742	1.050	0.154
1	0.957	1.315	0.179
1 1/4	1.278	1.660	0.191
1 1/2	1.500	1.900	0.200
2	1.939	2.375	0.218
2 1/2	2.323	2.875	0.276
3	2.900	3.500	0.300

Metric and custom sizes, as well as custom lengths can be accommodated. Laser etching identification can also be provided for traceability upon request.

Contact sales manager at lola.ramos@ametek.com or +1 302-382-1767.



42 MOUNTAIN AVENUE NESQUEHONING, PENNSYLVANIA, 18240-2201 U.S.A. TEL: +1 570-645-6917 • 800-441-7777 (U.S. and Canada only) FAX: +1 570-645-6950 www.ametekfpp.com

E-mail: info.fpp@ametek.com

should not be used. Please contact AMETEK for discussion of your specific process to be certain that our products are appropriate for your intended use. Adequate ventilation should be used where fluoropolymers are heated. Flu-like symptoms may occur from

conditions of pressure and temperature, or combinations of chemicals, fluoropolymer tubing

Fluoropolymer resins are generally considered inert to most chemicals. Under certain

exposure to vapors evolved from fluoropolymers at very high temperatures, up to 800°F or from smoking materials that contain particles of fluoropolymers. Symptoms pass within 48 hours and are the only adverse effects observed in humans to date. Unheated fluoropolymers are essentially inert and are nonirritating to the skin.

This information set forth herein is furnished free of charge and is based on technical data which AMETEK believes to be reliable. It is intended for use by persons having technical skill and at their own discretion and risk. Since conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with your use of this information. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.