



ARLON® 1330

PTFE-lubricated, Polyketone-based, High Performance Components

PLASTIC COMPONENTS

Greene, Tweed offers precision plastic components for a variety of demanding, semiconductor applications. These components are made from a full range of high-performance plastic materials including Arlon® 1330. Ideal for applications requiring exceptional wear resistance and chemical compatibility, Arlon 1330 provides good dimensional stability without the addition of carbon fibers.

FEATURES & BENEFITS

- Excellent chemical compatibility
- Low extractables
- Good dimensional stability
- Superior wear properties


APPLICATIONS

- CMP retainer Rings
- Guides
- Supports

TYPICAL PROPERTIES	
Physical	Typical Value
Color	Tan
Specific Gravity	1.38
Melt Point (Pellet), °F (°C)	649 (343)
Hardness, Shore D	85
Water Absorption, 24 hrs., %	0.35
Mechanical	
Tensile Break Strength, psi	12,600
Elongation, %	20
Flexural Strength, psi	21,100
Flexural 0.5% Secant Modulus, psi	535,000

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.

Prior to actual use it is recommended compatibility tests be run to determine suitability in a specific application. This is critical where failure could result in injury or damage. A regular program of inspection and replacement should be implemented. Greene, Tweed technical personnel are available to help with a recommendation.



TYPICAL PROPERTIES (cont.)	
Mechanical (cont.)	Typical Value
Compressive Strength @ Break, psi	15,500
Coefficient of Dynamic Friction PV=12,600 psi ft/min	0.15
Wear Factor, in ³ -min./lb-ft-hr x 10 ⁻¹⁰	20
Shear Strength @ Room Temperature	
Axial, psi	11,250
Transverse, psi	Not Applicable
Shear Strength @ 450°F (232°C)	
Axial, psi	2,870
Transverse, psi	Not Applicable
Izod Impact Strength	
Notched, ft-lb/inch	1.06
Unnotched, ft-lb/inch	18.74
Thermal	
Heat Distortion Temperature Under Load, @ 264 psi, °F (°C)	330 (165)
Coefficient of Thermal Expansion, <300°F (149°C), inch/inch per °F x 10 ⁻⁵	2.3
Coefficient of Thermal Expansion, >300°F (149°C), inch/inch per °F x 10 ⁻⁵	8.2

Contact Us

Greene, Tweed
Semiconductor
Kulpsville, PA, USA

Tel: +1.215.256.9521
Fax: +1.215.256.0189

Our Distributor

Banner Industries
High Purity Flow
Component Distribution
USA & Asia Pacific

Tel: +1.800.705.0016
Web: www.bannerindustries.com

