

AVALON[®] 56 HP High Purity Plastic Components for Wet Applications

PLASTIC COMPONENTS

Greene, Tweed offers precision plastic components designed for a variety of demanding semiconductor applications. Avalon® 56 HP — a high-performance plastic based on the latest generation modified PTFE—is ideal for improving the performance of wet wafer processing systems that require exceptional chemical resistance and very low extractable levels. In addition, Avalon 56 HP provides a very high level of purity, a wide temperature operating range, and superior low friction and dielectric properties.



FEATURES & BENEFITS

- Lower void content, less porosity and minimal permeability compared to standard PTFE
- Reduced cold flow resulting in longer service life compared to standard PTFE
- Extremely low extractable levels
- · Precision components available in a variety of configurations
- Lower costs of ownership and higher yields

APPLICATIONS

- Valve and pump components
- Manifolds
- Wafer carriers
- Fittings
- MSE[®] seals
- Low friction slide rails

TYPICAL PROPERTIES

| Physical | Typical Value |
|---|---------------|
| Color | White |
| Specific Gravity | 2.18 |
| Melt Point (Powder), °F (°C) | 626 (330) |
| Mechanical | |
| Tensile Strength, psi | 5000 |
| Elongation, % | 450 |
| Flexural 0.5% Secant Modulus, psi | 80,000 |
| Coefficient of Thermal Expansion, <300°F (149°C), inch/inch per °F x 10 ⁵ | 5.5 |
| Coefficient of Static Friction @ 33.3 psi and 150 fpm | 0.05 |
| Coefficient of Dynamic Friction PV=5000 psi ft/min | 0.08 |
| Wear Factor, in ³ -min./lb-ft-hr x 10 ⁻¹⁰ | 2500 |
| Permanent Deformation Under Load, 2000 psi @ 78°F (26°C), % | 3.2 |
| Shear Strength @ 80°F (27°C), psi | 2400 |
| Shear Strength @ 400°F (204°C), psi | 1350 |

Tel: +1.215.256.9521 Fax: +1.215.256.0189

Tel: +1.800.705.0016

Web: www.bannerindustries.com

BannerIndustries

Contact Us

Greene, Tweed Semiconductor Kulpsville, PA, USA

Our Distributor

Banner Industries High Purity Flow Component Distribution USA & Asia Pacific 2

< a

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.

Prior to actual use it is recommended compatibility tests be run to determine suitability in a specific application. This is critical where failure could result in injury or damage. A regular program of inspection and replacement should be implemented. Greene, Tweed technical personnel are available to help with a recommendation.



| EXTRACTABLES COMPARISON | | |
|-------------------------|--------------------------|--|
| ELEMENTS | AVALON 56 HP (ng/cm³) | STANDARD PTFE (ng/cm ³) |
| Mg | 0.28 | 2.58 |
| Al | 2.20 | 3.73 |
| Na | 0.67 | 18.10 |
| К | 0.55 | 18.40 |
| Са | 4.18 | 21.90 |
| Cr | 0.02 | 0.085 |
| Mn | 0.06 | 0.098 |
| Fe | 0.96 | 5.04 |
| Ni | < 0.50 | 0.63 |
| Cu | 0.09 | 21.40 |
| Zn | 0.28 | 6.43 |

AVALON® vs. PTFE 8 7 6 UNITS (ng/cm3) 5 4 3 2 0 Mg AL Cu Cr Mn Fe Zn Na Cu к Ni AVALON 56 HP STANDARD PTFE

Test conducted with 2% HNO₃ for 2 days @ 68°F (20°C).

പ

б

<u>---</u>

б

0

c t