

CHEMRAZ[®] 550 Carbon Loaded, Basic Perfluoroelastomer Seal Material

SEALING SOLUTIONS

Chemraz[®] 550 is recommended for use in wet systems where chemical compatibility is required and small amounts of contamination are acceptable. This seal material has a wide variety of uses in dynamic or static processing equipment applications with service temperatures up to 210°C (410°F).

FEATURES & BENEFITS

- · Good chemical resistance
- · Good physical properties
- Used where contamination requirements are less critical
- Excellent performance history

APPLICATIONS

- Valve seals
- Fitting and union seals
- Gaskets
- Regulator seals
- Filter seals

RECOMMENDED PROCESS APPLICATIONS

- Wet etch (acid, base)
- Wet stripping (solvents)
- Wet cleaning (UPDI)
- · Wet metal plating



•	
TYPICAL PROPERTIES*	
Physical	Typical Value
Color	Black
Polymer Type	Perfluoroelastomer
Specific Gravity	1.93
Hardness, Shore A	75
Mechanical	
Tensile Strength, psi (kPa)	1750 (12066)
Elongation, %	140
Tensile Modulus, psi (kPa)	
Modulus @ 50% Elongation	450 (3103)
Modulus @ 100% Elongation	1150 (7929)
Compression Set: 70 hours @ 204°C @ 25% Deflection, %	25
Thermal	
Service Temperature Range	-30°C to 210°C (-22°F to 410°F)

* Note: Unless otherwise indicated, all tests are performed on AS 568A (-214) O-rings.

Contact Us Greene, Tweed

Semiconductor Kulpsville, PA, USA

<u>Our Distributor</u>

Banner Industries High Purity Flow Component Distribution USA & Asia Pacific Tel: +1.215.256.9521 Fax: +1.215.256.0189

Tel: +1.800.705.0016 Web: www.bannerindustries.com

BannerIndustries

© 2005, Greene, Tweed all rights reserved All trademarks are property of their respective owners. 05/05-GT DS-US-SC-043

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.

Prior to actual use it is recommended compatibility tests be run to determine suitability in a specific application. This is critical where failure could result in injury or damage. A regular program of inspection and replacement should be implemented. Greene, Tweed technical personnel are available to help with a recommendation.